



# Technical Data Sheet

## *Spray Plast* Level 5 Primer/Surfacer

Resin Type	Vinyl Acrylic
Gloss	Flat
Color	White or Off White
Weight per Gallon	12.5 lb/gal
Recommended Coverage	100 – 150 ft <sup>2</sup> per gallon
Wet Film Thickness	14-16 mils
Dry Time	(75° F / 50% RH) To touch: 1 – 2 hours Recoat: Overnight
Fire Rating	0
Mildew Resistance	10 (ASTM D-3273)
Flash Point	> 200° F
VOC	.26 lbs/gal 31.2 g/l
Cleanup	Water

### Submittal Approvals

Job Name:	
Job Location:	
Contractor:	
Approved By:	Date:

Manufactured by:  
TWI  
300 West Norton Ave.  
Eustis, FL 32726  
(800) 331-8273  
[www.twidursystem.com](http://www.twidursystem.com)