



# Technical Data Sheet

## DS 3000

### 100% Acrylic Texture Coating

Resin Type	100% Acrylic
Gloss	Flat
Color	White (up to 8 oz. universal colorant per 5 gallons)
Weight per Gallon	13 lb/gal
Viscosity	500 BU
% Solids by Weight	63 ± 2%
% Solids by Volume	42 ± 2%
Permeability	16.9 (ASTM D-1653)
Mildew Resistance	10 (ASTM D-3273)
Recommended Coverage	100 – 125 ft <sup>2</sup> per gallon
Wet Film Thickness	16 mils @ 100 ft <sup>2</sup> per gallon
Dry Film Thickness	7 mils @ 100 ft <sup>2</sup> per gallon
Dry Time	(75° F / 50% RH) To touch: 2 – 4 hours Recoat: 6 – 8 hours
Fire Rating	0
Flash Point	> 200° F
Flame Spread	5 (ASTM E-84)
Smoke Development	0 (ASTM E-84)
VOC	.41 lbs/gal 49.2 g/l
Cleanup	Water

### Submittal Approvals

<b>Job Name:</b>	
<b>Job Location:</b>	
<b>Contractor:</b>	
<b>Approved By:</b>	<b>Date:</b>

Manufactured by:  
 TWI  
 300 West Norton Ave.  
 Eustis, FL 32726  
 (800) 331-8273

[www.twidursystem.com](http://www.twidursystem.com)