



CT 200

Interior Latex Flat

Product Line:
Color Train Paint

Product Name:
CT 200 Interior Latex Flat Wall Paint

Manufacturer:
Tool World, Inc.
300 W. Norton Ave.
Eustis, FL 32726
☎ (800) 331-8273
☎ (352) 357-8282
FAX (352) 357-1417

Product Description:
Color Train CT200 Interior Latex Flat is a high hiding, washable latex paint which provides a durable finish coat. An ideal top coat for the Color Train **CT700 & CT750 Primers**.

CT200 can also be applied over drywall, plaster, masonry, and properly prepared wood and metal surfaces.
Packaging: Available in Quarts, Gallons, 5 gallon buckets.
Colors: Available in a wide variety of colors.

Surface Preparation

Previously painted surfaces shall be clean, dry, and free of dust, grease, wax and gloss.
1. Wash surface with water and detergent.
2. After washing, sand glossy areas and rinse.
3. Patch cracks; sand when dry.
4. Let dry completely before applying **CT200**.

Unpainted Plaster, Drywall, and Masonry Surfaces shall be clean, dry, and free of dust, grease, wax, and gloss. Prime with **CT750 or CT700**. For level 5 smooth finish surfaces, prime with **Spray-Plast Wall Surfacer** in lieu of **CT700**. For new plaster, allow 20 days curing time before applying primer.

Unpainted Wood Surfaces: Prime with an alkyd primer. Let dry completely before applying **CT200**.

Unpainted Metal Surfaces: Prime with a rust inhibiting metal primer. Let dry completely before applying **CT200**.

Application, Equipment:

Apply with nylon or polyester brush, roller, pad, or sprayer (air or airless). Do not apply at room temp. below 50° F. For greater assurance of uniform color, intermix two or more buckets of same color paint. Apply a second coat for additional durability (allow two hours before recoating).

Use a respirator approved by U.S. Bureau of Mines.

Clean tools, equipment, and skin with soapy water and rinse.

Coverage:

Coverage will vary according to surface porosity, and equipment. Average Coverage: 300 sq.ft./gal.

Mixing and Cleaning:

Stir material thoroughly. If thinning is necessary, thin with clean water. Do not exceed 1 pint per gallon.

FORMULA ANALYSIS

PIGMENT:	36%
Titanium Dioxide	36%
Aluminum Silicate	44%
Mica	6%
Diatom. Earth	6%
Calcium Carb.	8%
TOTAL	100%
VEHICLE:	64%
Acrylic Vinyl	
Copolymer	27%
Water & Glycol	70%
Mildewcide & Wetting Agent	3%
TOTAL	100%

PRODUCT DATA:

Type of Pigment: Titanium Dioxide, Aluminum Silicate
Mica
Diatomaceous Earth
Calcium Carbonate
Type of Vehicle: Acrylic-Vinyl Copolymer
Solvent-Thinner Water, Ethylene Glycol
Clean-Up: Water
Packaging: Quart, Gallon, 5-Gallons
% Solids by Wt: 45.0
% Solids by Vol: 28.0
Weight per Gallon: 11.2 lb
Pigment Volume
Conc. (PVC) 58%

5 Year Warranty: If **CT200 Interior Latex Flat WP** fails to perform as specified, when applied according to label directions, Tool World's obligation shall be limited to refund of purchase price. Sales slip must accompany evidence of failure.

