



CT 400

Int-Ext Latex S/G Enamel

Product Line:
Color Train Paint

Product Name:
CT 400 Int-Ext Latex Semi-Gloss Enamel

Manufacturer:
Tool World, Inc.
300 W. Norton Ave.
Eustis, FL 32726
☎ (800) 938-7839
☎ (352) 357-8282
FAX (352) 357-1417

Product Description:
Color Train 400 Int-Ext Latex S/G Enamel is a semi-gloss paint which provides a durable, easy to clean finish coat. An ideal top coat for the Color Train **CT700 & CT750 Primers**.

CT400 can also be applied over drywall, plaster, masonry, and properly prepared wood and metal surfaces.
Packaging: Available in Quarts, Gallons, 5 gallon buckets.
Colors: Available in a wide variety of colors.

Surface Preparation

Previously painted surfaces shall be clean, dry, and free of dust, grease, wax and gloss.
1. Wash surface with water and detergent.
2. After washing, sand glossy areas and rinse.
3. Patch cracks; sand when dry.
4. Let dry completely before applying **CT400**.

Unpainted Plaster, Drywall, and Masonry Surfaces shall be clean, dry, and free of dust, grease, wax, and gloss. Prime with **CT750 or CT700**. For level 5 smooth finish surfaces, prime with **Spray-Plast Wall Surfacer** in lieu of **CT700**. For new plaster, allow 20 days curing time before applying primer.

Unpainted Wood Surfaces: Prime with an alkyd primer. Let dry completely before applying **CT400**.

Unpainted Metal Surfaces: Prime with a rust inhibiting metal primer. Let dry completely before applying **CT400**.

Application, Equipment:

Apply with nylon or polyester brush, roller, pad, or sprayer (air or airless). Do not apply at room temp. below 50° F. For greater assurance of uniform color, intermix two or more buckets of same color paint. Apply a second coat for additional durability (allow two hours before recoating).

Use a respirator approved by U.S. Bureau of Mines.

Clean tools, equipment, and skin with soapy water and rinse.

Coverage:

Coverage will vary according to surface porosity, and equipment. Average Coverage: 300 sq.ft./gal.

Mixing and Cleaning:

Stir material thoroughly. If thinning is necessary, thin with clean water. Do not exceed 1 pint per gallon.

FORMULA ANALYSIS

PIGMENT: 23%
Titanium Dioxide 71%
Aluminum Silicate 21%
Calcium Carb. 8%
Total 100%

VEHICLE: 77%
Acrylic Vinyl Copolymer 55%
Water & Glycol 40%
Wetting Agent 5%
Total 100%

PRODUCT DATA:

Type of Pigment: Titanium Dioxide, Aluminum Silicate
Type of Vehicle: Acrylic-Vinyl copolymer
Solvent-Thinner: Water, Ethylene Glycol
Weight per Gallon: 10.5 lb
Clean-Up: Water
Packaging: Quarts, Gallons, 5 gallons
% Solids by Wt. 46.7
% Solids by Vol. 35.2
Pigment Volume Conc. (PVC) 24%

5 Year Warranty: If **CT400 Interior Latex S/G Enamel** fails to perform as specified, when applied according to label directions, Tool World's obligation shall be limited to refund of purchase price. Sales slip must accompany evidence of failure.

