



Technical Data Sheet

DS 4000

100% Acrylic Texture Coating

Resin Type	100% Acrylic
Gloss	Flat
Color	White (up to 8 oz. universal colorant per 5 gallons)
Weight per Gallon	13 lb/gal
Viscosity	500 BU
% Solids by Weight	63 $\pm$ 2%
% Solids by Volume	44 $\pm$ 2%
Scrub Resistance	2,670 cycles (ASTM D-2486)
Permeability	16.9 (ASTM D-1653)
Mildew Resistance	10 (ASTM D-3273)
Recommended Coverage	100 – 125 ft ² per gallon
Wet Film Thickness	16 mils @ 100 ft ² per gallon
Dry Film Thickness	7 mils @ 100 ft ² per gallon
Dry Time	(75° F / 50% RH) To touch: 2 – 4 hours Recoat: 6 – 8 hours
Fire Rating	0
Flash Point	> 200° F
Flame Spread	5 (ASTM E-84)
Smoke Development	0 (ASTM E-84)
VOC	.41 lbs/gal 49.2 g/l
Cleanup	Water

Submittal Approvals

Job Name:	
Job Location:	
Contractor:	
Approved By:	Date:

Manufactured by:

TWI

300 West Norton Ave.

Eustis, FL 32726

(800) 331-8273

www.twidursystem.com